

**AMENDMENTS TO THE CLAIMS**

1. (Currently Amended) A metal golf club head, comprising:  
a ball hitting face made of a metal, which includes a central portion and  
a peripheral portion surrounding at least a part of said central portion,  
wherein the hardness of the metal at said peripheral portion is lower  
than the hardness of the metal at said central portion.

2. (Previously Presented) A metal golf club head, comprising:  
a face member forming a ball hitting face, said ball hitting face  
including a central portion and a peripheral portion surrounding at least a part of  
said central portion,  
wherein said golf club head is manufactured by a method comprising  
the steps of:  
forming said face member from a raw material separately from other  
members used for said golf club head; and  
subsequently welding said other members to said face member at a  
periphery of said face member, and  
the hardness of the metal at said peripheral portion is smaller than the  
hardness of the metal at said central portion.

3. (Previously Presented) A golf club head according to claim 1,  
wherein  
the width of said peripheral portion of said hitting face is in a range  
between about 5 and 20 mm, the width of said peripheral portion being determined  
by:

measuring a hardness distribution of said hitting face from an arbitrary point A on the edge of said hitting face, passing through the center of said hitting face, to a point B on the opposite edge of said hitting face;

determining the hardness of said central portion by taking an average of the hardness measured in an area in the vicinity of the center of said hitting face where the difference in hardness in the area is in the range of  $\pm 5\%$ ;

determining the hardness of said peripheral portion in the vicinity of the point A by taking an average of the hardness measured in an area in the vicinity of the point A where the difference in hardness in the area is in the range of  $\pm 5\%$ ;

determining a point of measurement having a value of hardness closest to a mean value between the hardness of said central portion and the hardness of said peripheral portion; and

determining the width of said peripheral portion as a distance between the point A and the point of measurement.

4. (Previously Presented) A golf club head according to claim 2, wherein

the width of said peripheral portion of said hitting face is in the range between about 5 and 20 mm, the width of said peripheral portion being determined by:

measuring a hardness distribution of said hitting face from an arbitrary point A on the edge of said hitting face, passing through the center of said hitting face, to a point B on the opposite edge of said hitting face;

determining the hardness of said central portion by taking an average of the hardness measured in an area in the vicinity of the center of said hitting face where the difference in hardness in the area is in the range of  $\pm 5\%$ ;

determining the hardness of said peripheral portion in the vicinity of the point A by taking an average of the hardness measured in an area in the vicinity of the point A where the difference in hardness in the area is in the range of  $\pm 5\%$ ;

determining a point of measurement having a value of the hardness closest to a mean value between the hardness of said central portion and the hardness of said peripheral portion; and

determining the width of said peripheral portion which is a distance between the point A and the point of measurement.

5. (Original) A golf club head according to claim 1, wherein the difference in the hardness between said central portion and said peripheral portion is equal to or greater than 50 in terms of the Vickers hardness, the hardness of said central portion and of said peripheral portion being determined by:

measuring a hardness distribution of said hitting face from an arbitrary point A on the edge of said hitting face, passing through the center of said hitting face, to a point B on the opposite edge of said hitting face;

determining the hardness of said central portion by taking an average of the hardness measured in an area in the vicinity of the center of said hitting face where the difference in hardness in the area is in the range of  $\pm 5\%$ ; and

determining the hardness of said peripheral portion in the vicinity of the point A by taking an average of the hardness measured in an area in the vicinity of the point A where the difference in hardness in the area is in the range of  $\pm 5\%$ .

6. (Original) A golf club head according to claim 2, wherein

the difference in the hardness between said central portion and said peripheral portion is equal to or greater than 50 in terms of the Vickers hardness, the hardness of said central portion and of said peripheral portion being determined by:

measuring a hardness distribution of said hitting face from an arbitrary point A on the edge of said hitting face, passing through the center of said hitting face, to a point B on the opposite edge of said hitting face;

determining the hardness of said central portion by taking an average of the hardness measured in an area in the vicinity of the center of said hitting face where the difference in hardness in the area is in the range of  $\pm 5\%$ ; and

determining the hardness of said peripheral portion in the vicinity of the point A by taking an average of the hardness measured in an area in the vicinity of the point A where the difference in hardness in the area is in the range of  $\pm 5\%$ .

Claim 7. (Original) A golf club head according to claim 3, wherein the difference in the hardness between said central portion and said peripheral portion is equal to or greater than 50 in terms of the Vickers hardness, the hardness of said central portion and of said peripheral portion being determined by:

measuring a hardness distribution of said hitting face from an arbitrary point A on the edge of said hitting face, passing through the center of said hitting face, to a point B on the opposite edge of said hitting face;

determining the hardness of said central portion by taking an average of the hardness measured in an area in the vicinity of the center of said hitting face where the difference in hardness in the area is in the range of  $\pm 5\%$ ; and

determining the hardness of said peripheral portion in the vicinity of the point A by taking an average of the hardness measured in an area in the vicinity of the point A where the difference in hardness in the area is in the range of  $\pm 5\%$ .

8. (Withdrawn)

9. (Withdrawn)

10. (Withdrawn)

11. (Withdrawn)

12. (Withdrawn)

13. (New) The golf club head according to claim 1, wherein said ball hitting face is subjected to an aging process before welding said face member to other members used for said golf club head.

14. (New) The ball hitting face according to claim 1, wherein said ball hitting face is made of titanium alloy.

15. (New) The ball hitting face according to claim 1, wherein said ball hitting face is made from a metal whose strength is increased by being subjected to heating, and when said metal is welded whose strength of the welded portion is decreased.

16. (New) The golf club head according to claim 2, wherein said face member is subjected to an aging process before said face member is welded to said other members.

17. (New) The face member according to claim 2, wherein said face member is made of titanium alloy.

18. (New) The golf club head according to claim 3, wherein said face member is made from a metal whose strength is increased by being subjected to an aging process, and when said metal is welded whose strength of the welded portion is decreased.